

Internal Product Specification Sheet

ULTRA-MATE® Brand Hook

Material Description

Name: HTH 889 / Loop 3610

Material: FR Polypropylene base resin and Nylon Loop

Dimensional Specifications

Roll Length: <100 yards (-0, +12 inches)

=/>100 yards (-0, +1% of target value)

Performance Specifications

Testing	Minimum	Test Method
Peel Strength	0.3 PIW	40011
Flammability – 12 Second Vertical	Burn Length, 8", max Flame Time, 15 sec, max Drip Time, 5 sec, max	FAR 25.853 (b)
Flammability – 60 Second Vertical	Burn Length, 6", max Flame Time, 15 sec, max Drip Time, 3 sec, max	FAR 25.853 (a)
Flammability - MVSS 302, 15 Second Horizontal	Burn Rate Max.: <2.5" per min.	MVSS302 (15s)

Tested Against Itself (L3610)

The preparation, testing and conditioning follow the Velcro USA Inc. Quality Control Laboratory Standard Procedures.

Note: The following information should be considered representative and is intended to be used as a reference only. This information should not be used for specification purposes.

Rev. Date: 9.17.15

95 Sundial Ave • Manchester, New Hampshire 03103 Telephone: (603) 669-4880 • Fax: (603) 669-3086

¹ Contact your Customer Relations Specialist for available colors and widths